



ZHONGDING

SERENITY

100%UNDYED CASHMERE

2/26Nm

SERENITY

100%UNDYED CASHMERE

2/26Nm

天然原色山羊绒 | 柔滑软糯

每公斤纱线碳足迹为51.9300 kgCO₂e

Natural Undyed Cashmere | Exquisitely Soft and Velvety

Carbon Footprint per KG of Yarn: 51.9300 kgCO₂e

SERENITY

成份: 100%ECO山羊绒

支 数: 2/26Nm - 12 针

颜色: 10色

后整理: 在两次洗缩过程中, 使用专用助剂可以获得更佳的手感。第一次水洗旨在清除纺纱时使用的和毛油助剂和染色过程中遗留的浮色。第二次洗涤主要用于调整织物的手感。

水温: 30°C

浴比: 1:25

第一次水洗:

- ◆ 根据衣服的重量, 加入2%蓬松剂
- ◆ 浸泡30分钟, 适时翻身转动使样衣受助剂均匀
- ◆ 转动6-10分钟, 可根据需要调整转动时间以满足手感要求
- ◆ 漂洗及脱水

第二次水洗:

- ◆ 根据衣服的重量, 加入4%的柔软剂
- ◆ 浸泡20分钟, 适时转动, 可根据需要调整时间以满足手感要求
- ◆ 漂洗及脱水
- ◆ 75°C标准转笼烘干(浅亮色建议 60°C)

色牢度: 若选用颜色对比强烈的条纹织物, 请注意特别的色牢度要求

备注:

色卡内所有颜色均可提供样纱服务。

订单量低于50KG/色将加收取20%附加费。

客户特殊颜色具体起订量及附加费请洽业务部门咨询。



手洗



请勿漂白



低温熨烫



干洗



平摊晾干

COMPOSITION: 100%Undyed Cashmere

COUNT: 2/26Nm - 12 Gauge

COLOR: 10 Colors

RECOMMENDED FINISHING:

Utilizing specialized detergent during the two bath processes can enhance the handfeel. The initial wash aims at removing sizing agents, spin finishes, and residual dyestuffs from the dyeing and spinning processes, while the subsequent wash aims to enhance the handfeel of the fabric.

Water temperature: 30°C

Liquor ratio: 1:25

BATH 1:

- ◆ Add 2% fluffy agent according to the weight of the garment
- ◆ Soak for 30 minutes, gently stir to ensure an even distribution of additives
- ◆ Rotate for 6-10 minutes, modifying the rotation duration to attain the preferred handfeel
- ◆ Rinse and drain

BATH 2:

- ◆ Add 4% softener according to the weight of the garment
- ◆ Soak for 20 minutes with gentle rotating. Adjust the duration as needed to achieve preferred handfeel
- ◆ Rinse and drain
- ◆ Standard tumble dry at 75°C (60°C recommended for light shades)

COLOUR FASTNESS:

For contrasting striped fabrics, please adhere to specific color fastness requirements

REMARKS:

Sample yarn service is available for all colours on the colourcard.

Orders below 50KG/color will incur a 20% surcharge.

MOQ and surcharge for special colors, please contact the sales representatives.



Hand Wash



Do Not Bleach



Iron Low



Dry Clean



Dry Flat


SERENITY

2/26Nm 100%Undyed Cashmere

12gg 1ply



ZHONGDING



SERENITY

2/26Nm 100%Undyed Cashmere

7gg 2ply



ZHONGDING



A




RESTORE
C30001•

B



SKIN
C30006•



APPLE CINNAMON
C30002•



GRAY SAND
C30007•



RAW ALMOND
C30003•



WINTER DAWN
C30008•



ZHONGDING

C



HEMP
C30004•

D



CAMEL
C30009•



CEMENT
C30005



PIER
C30010✿



ZHONGDING

SERENITY

Color Code	Column#	Color Code	Column#
C30001•	A1	C30008🌸•	B3
C30002•	A2	C30004•	C1
C30003🌸	A3	C30005	C2
C30006🌸•	B1	C30009•	D1
C30007•	B2	C30010🌸	D2

"•" 大货库存色 Available for bulk stock
"🌸" AB纱 Marl yarn

支持选用指定原料定制，详情请咨询销售代表。
Customization available with specified materials. Please contact our sales representatives for details.



CHINA OFFICE

- **Zhejiang Zhongding Textile Co., Ltd.**
No. 388 Zhongshan Road, Chongfu Industrial Zone,
Tongxiang City, Zhejiang Province, China
TEL: +86 573 8822 8888
EMAIL: service@zdtex.com

HONG KONG OFFICE

- **Zhongding International Development Ltd.**
Room 1007, 10/F Saxon Tower,
7 Cheung Shun Street, Lai Chi Kok,
Kowloon, Hong Kong
TEL: +852 3565 5216
EMAIL: matthew@zdtex.com

JAPAN OFFICE

- **Italo.fil**
5-17-6 Minami Aoyama,
Minato-Ku, Tokyo 107-0062, Japan
TEL: +34 609 804 641
EMAIL: nakamura@italo-fil.co.jp

UNITED KINGDOM OFFICE

- **Zhong Ding Int (UK) Company Ltd.**
54, Chaveney Road,
Quorn, Leicestershire,
LE12 8AD, UK
TEL: +44 780 327 7088
EMAIL: richard@zdint.co.uk

GERMANY OFFICE

- **Zhong Ding Int GmbH.**
Stolco Haus, DFC Dialog Büro,
Steinstraße 16-18,
Düsseldorf, D-40212, Germany
TEL: +39 348 155 3609
EMAIL: richard@zdint.co.uk

SPAIN OFFICE

- **Zhong Ding Int.**
Via Augusta 236, 5B,
08021 Barcelona, Spain
TEL: +34 609 804 641
EMAIL: sara@zdint.co.uk