

ZHONG/ /DING

LITHE

55%TENCEL™ LYOCCELL 40%EXTRAFINE MERINO WOOL 5%SILK

2/48Nm 2/60Nm

LITHE

2/48Nm 2/60Nm

55%天丝™莱赛尔 40%超细美丽诺羊毛 5%桑蚕丝

55%TENCEL™Lyocell 40%Extrafine Merino Wool 5%Silk

19.5μm 丝光羊毛
19.5μm Mercerized Wool

天丝™莱赛尔
TENCEL™Lyocell

可轻柔机洗
Gentle Machine Washable

LITHE



成份：

55%天丝™莱赛尔
40%超细美丽诺羊毛*
5%桑蚕丝

*19.5µm 丝光羊毛

支数及颜色：

2/48Nm - 14/16针 - 30 色
2/60Nm - 16/18针 - 3 色



了解更多

Composition:

55%TENCEL™Lyocell
40%Extrafine Merino Wool*
5%Silk

*19.5µm Mercerized Wool

Count & Color:

2/48Nm - 14/16gg - 30 Colors
2/60Nm - 16/18gg - 3 Colors



Learn More

后整理：

在两次洗缩过程中，使用专用助剂可以获得更佳的手感。第一次水洗旨在清除纺纱时使用的和毛油和染色过程中遗留的浮色。第二次洗涤主要用于调整织物的手感。以下后整理方法只供参考，可根据需要的手感调整洗涤剂用量、浸泡时间及转动时长。

水温：30°C **浴比：**1:25

第一次水洗：

根据衣物重量加入1%的洗涤剂，浸泡3分钟后转动1分钟，最后进行漂洗及脱水。

第二次水洗：

根据衣物重量加入2%的柔软剂，浸泡30分钟后转动2-3分钟。最后进行脱水，并在75-80°C下标准转笼烘干（浅亮色衣物建议60°C）。

色牢度：

若选用颜色对比强烈的条纹织物，请注意特别的色牢度要求。

备注：

纱线支数差异可能导致色差，颜色以实物为准。

色卡内所有颜色均可提供样纱服务。

客户色散毛染色最低起订量为20KG/色；订单量低于50KG/色将加收收取20%附加费。

Recommended Finishing:

For optimal handfeel, use the specialized detergent in the two-bath process. The first bath is aimed at removing spin finishes, sizing agents, and residual dyestuffs, while the subsequent bath refines the final fabric handfeel. The following parameters are for reference only; Adjust detergent dosage, soaking and rotation time based on the desired handfeel.

Water Temperature: 30°C **Liquor Ratio:** 1:25

First Wash:

Add 1% detergent by garment weight. Soak for 3 minutes, then rotate for 1 minute. Finally, rinse and spin.

Second Wash:

Add 2% softener by garment weight. Soak for 30 minutes, then rotate for 2-3 minutes. Spin and standard tumble dry at 75-80°C (60°C is recommended for bright/light colors).

Color Fastness:

For fabrics with high-contrast stripes, please pay attention to colorfastness requirements.

Remarks:

Color may vary with yarn count. Please refer to the actual product for the final color.

Sample yarn service is available for all colors on the colorcard.

MOQ for custom color in fiber dyeing: 20KG/color. Orders below 50KG/color will incur a 20% surcharge.


LITHE

2/48Nm 55%TENCEL™ LYOCELL 40%EXTRAFINE MERINO WOOL 5%SILK

16gg



ZHONGDING



A



EGGWHITE
T0001★

B




CLAM
T0006

C



SOUFFLE
T0011




FEATHER
T0002




OATS
T0007




CHEDDAR
T0012




GLITCH
T0003★




RYE
T0008



BUTTERNUT
T0013



CAST IRON
T0004




CHIPMUNK
T0009




CARDINAL
T0014



MOONLESS
T0005★



MANE
T0010



FIREWOOD
T0015



ZHONGDING

D



LIMONCELLO
T0016

E



DROPLET
T0021

F




CANDY FLOSS
T0026




HERB
T0017



OCEANIC
T0022




PEONY
T0027



SPRUCE
T0018



PROFOUND
T0023




AUBERGINE
T0028



SEPAL
T0019




NORTHERN
T0024



UBE
T0029



HUNTER
T0020



HAVRAN
T0025



CURRANT
T0030



ZHONGDING

LITHE

New Color Code	Original Color Code	Column#	New Color Code	Original Color Code	Column#	New Color Code	Original Color Code	Column#
T0001★	ZQ011043★	A1	T0011	ZQ111053	C1	T0021	ZQ511063	E1
T0002	ZQ711044	A2	T0012	ZQ121054	C2	T0022	ZQ531064	E2
T0003★	ZQ721045★	A3	T0013	ZQ121055	C3	T0023	ZQ631066	E3
T0004	ZQ731046	A4	T0014	ZQ431056	C4	T0024	ZQ231067	E4
T0005★	ZQ741047★	A5	T0015	ZQ321057	C5	T0025	ZQ531068	E5
T0006	ZQ311048	B1	T0016	ZQ211058	D1	T0026	ZQ411069	F1
T0007	ZQ311049	B2	T0017	ZQ221059	D2	T0027	ZQ421070	F2
T0008	ZQ321050	B3	T0018	ZQ221060	D3	T0028	ZQ611071	F3
T0009	ZQ321051	B4	T0019	ZQ221061	D4	T0029	ZQ621072	F4
T0010	ZQ331052	B5	T0020	ZQ231062	D5	T0030	ZQ431073	F5

★ 提供 2/48Nm 及 2/60Nm 支数 | Available in both 2/48Nm & 2/60Nm yarn counts.

认证与品牌素材支持
Certification & Brand Materials Support



其他认证
Other Certifications



支持选用指定原料进行定制
Customization available with specified materials



供应商吊牌*
Supplier Hangtag



防伪吊牌 | 可轻柔机洗羊毛
Authenticity Hangtag
Gentle Machine Washable Wool

*TENCEL™ 和天丝™ 是Lenzing AG的商标
TENCEL™ and LENZING™ are trademarks of Lenzing AG

CHINA OFFICE

- **Zhejiang Zhongding Textile Co., Ltd.**
No. 198, Hangfu Road, Chongfu Industrial Park,
Tongxiang City, Zhejiang
TEL: +86 573 8822 8888
EMAIL: service@zdtex.com

HONG KONG OFFICE

- **Zhong Ding International Development Ltd.**
Room 1007, 10/F Saxon Tower,
7 Cheung Shun Street, Lai Chi Kok,
Kowloon, Hong Kong
TEL: +852 3565 5216
EMAIL: matthew@zdtex.com

JAPAN OFFICE

- **Italo-Fil Co., Ltd.**
Aoyama Green Heights 205
5-17-6 Minami Aoyama,
Minato-Ku, Tokyo 107-0062, Japan
TEL: +03 5464 2577
EMAIL: nakamura@italo-fil.co.jp

USA OFFICE

- **Zhong Ding USA**
525 7th Avenue, Suite 1008
New York, NY 10018
TEL: +917 345 9630
EMAIL: paolo.fontana@aeffefilati.com

UK OFFICE

- **Zhong Ding Int (UK) Company Ltd.**
54, Chaveney Road,
Quorn, Leicestershire,
LE12 8AD, UK
TEL: +44 780 327 7088
EMAIL: richard@zdint.co.uk

GERMANY OFFICE

- **Zhong Ding Int GmbH.**
Stolco Haus, DFC Dialog Büro,
Steinstraße 16-18,
Düsseldorf, D-40212, Germany
TEL: +39 348 155 3609
EMAIL: richard@zdint.co.uk

SPAIN OFFICE

- **Zhong Ding Int.**
Via Augusta 236, 5B,
08021 Barcelona, Spain
TEL: +34 609 804 641
EMAIL: sara@zdint.co.uk